

4835 Hollywood Boulevard Suite 4, Hollywood, FL 33021 - P: +1 305-709-7256

CG-21-46 Polyalkylene Glycol (PAG) Compressor Oil ISO 46

CG-21-46 offers full compatibility with most OEM polyalkylene glycol (PAG) compressor lubricants. This compatibility means that flushing of the existing compressor oil is not necessary to change to CG-21-46, reducing maintenance costs and downtime. CG-21-46 offers superb resistance against water contamination and an extended service life of 10,000 hours.

ATTRIBUTES

- 10,000-hour oil life at 100°C discharge temperature
- · Compatible with most OEM PAG compressor lubricants
- Resists water contamination
- · Protects against wear, rust and corrosion
- Non-toxic/non-hazardous

TYPICAL LUBRICANT PROPERTIES

CG-21-46 Grades	32	46	68
Viscosity cSt @ 40°C	32	46.1	67
Viscosity cSt @ 100°C	5.4	6.7	8.7
Flash Point °F (°C)	435 (224)	450 (232)	478 (248)
Copper Corrosion	1a	1a	1a
Rust Test: Distilled Water	Pass	Pass	Pass
Rust Test: Salt Water	Pass	Pass	Pass
Foam Sequence I, II, III	0/0/0	0/0/0	0/0/0

Page 1 of 1

CG-21-46 - Revised 05/2018

The information on Chemicals Global and competitive products provided should only be used as a general guide. Lubricant properties are typical results and should not serve as a sole resource for determining the correct lubricant for a particular application. Please consult a Chemicals Global representative to ensure that the product is the correct choice for the application.